

## Merbenit HS60

**Merbenit HS60 is a high modulus, elastic adhesive with high strength. Adheres thanks SMP base to various materials. Merbenit HS60 is also approved for use in foodstuff related areas as well as for ventilation systems.**

### Technical data

Shore A hardness, DIN 53505	60
Modulus elongation at 100%, DIN 53504 S2	ca. 1.6 N/mm <sup>2</sup>
Elongation at break, DIN 53504 S2	ca. 250%
Tensile strength, DIN 53504 S2	ca. 2.3 N/mm <sup>2</sup>
Consistency	stable
Tooling time	max. 10 min.
Curing rate after 24h	≥ 2.0 mm
Curing rate after 48h	≥ 3.0 mm
Density	1.54 ± 0.05 g/cm <sup>3</sup>
Volume change, DIN EN ISO 10563	≤ 8%
Temperature resistance after curing	- 40 °C to + 90 °C
Application temperature	+ 5 °C to + 40 °C
Shear strength	2.1 N/mm <sup>2</sup>

All measurements were performed under normal conditions (23 °C and 50 % relative humidity).

### Application

Flexible bonding in the areas of metal, apparatus and machine construction, plastics technology, air-conditioning and ventilation systems, car body, wagon, vehicle and container construction. Bonding in areas of food processing industries.

### Substrate range

Suitable materials are metals, powder-coated, varnished, galvanised, anodised, chromed or hot zinc dipped surfaces, various plastics, ceramics, stone, concrete and wood. Due to the large variety of different plastics and compositions as well as materials which are susceptible cracks, preliminary tests are recommended.

### Meets the standards

- AC-plants according to VDI 6022
- ISEGA (food production area)
- eco-bau 1st priority ECO-BKP

# Technical data sheet Merbenit HS60

## Substrate preparation

To achieve reproducible results the substrate has to be pre-treated according to the state of technology. All undefined surfaces must be removed using suitable methods. Apply the adhesive/sealant promptly to the prepared surface. Depending on the substrate and the expected requirements a mechanical or chemical pre-treatment is recommended respectively cleaning with rubbing alcohol, isopropanol or acetone. For application the surface has to be clean, durable and free of dust, oil and grease.

## Adhesion promoter

With most materials a good adhesion is achieved even without adhesion promoter. In the case of high moisture influence we recommend our Adhesion Promoter V40 on non-porous materials, Adhesion Promoter V21 on open porous materials. For thermopainted or powder-coated surfaces we recommend our Adhesion Promoter V40. In the case of special plastics an improvement of the adherence can be achieved with Adhesion Promoter V30. Preliminary tests are recommended.

## Processing

- Can be applied directly from the cartridge / sausage using a suitable caulking gun (manual, air, battery)
- Cut the nozzle tip according to the joint width
- V-Nozzles are recommended for bonding applications
- Depending on the bonding surface, material expansion, tension and mechanical stresses a layer thickness of 1 - 6 mm is recommended
- Can be applied with automatic dispensing equipment
- For vapor permeable substrates the material can be applied in a large area using a notched trowel
- The bonding must take place within the processing time
- Non-cured adhesive can be removed with rubbing alcohol or isopropanol
- Cured adhesive can only be removed mechanically

## Paint compatibility

Due to the diversity of varnishes and paints on the market we recommend preliminary tests. Using paints based on alkyd resins may delay the drying process. After cleaning with acetone joints can be varnished at any time. For burning process the material can be exposed, when fully cured, in short term to elevated temperatures.

## Chemical resistance

- Good against water, aliphatic solvents, oils, grease, diluted inorganic acids and alkalis
- Moderate against esters, ketone and aromatics
- Not resistant against concentrated acids and chlorinated hydrocarbons

## Colours

- black
- grey
- white
- other colours on request

## Packaging

- Cartridges of 290 ml in carton of 12 units
- Sausages of 600 ml in carton of 12 units

## Shelf life and storage conditions

- 18 months from date of production
- Store cool and dry
- Further information on request

## Work and environmental safety

Important information about work and environmental safety is available on the material safety data sheet.

**merz+benteli ag**

Freiburgstrasse 616  
CH - 3172 Niederwangen  
Tel. +41 31 980 48 48  
Fax +41 31 980 48 49  
info@merz-benteli.ch  
www.merz-benteli.ch

Our information is based on experiences in lab and practice. Their publication occurs, however, without takeover of a liability for damages and losses which are to be put down to these information, as there the practical application conditions are lying outside of the enterprise's control. The user is not released from the necessity to carry out own attempts for the planned applications under practical conditions. Due to the different materials, processing methods and local factors onto which we have no influence, no guarantee – also in patent-legal respect – can be taken over. We recommend therefore sufficient own attempts. By the way we refer to our General Business Conditions. Technical changes reserved. Contents examined and released by merz+benteli ag, CH - Niederwangen/Berne

