Technical Datasheet





Product Description

Panacol Elecolit[®] adhesives are solvent free single or two-component adhesives. They are mostly based on epoxy resin and can be cured at room temperature or by exposure of heat. Elecolit[®] adhesives are electrically and / or thermally conductive adhesives which are designed for potting, bonding or contacting of conductors.

Elecolit[®] 327 is a silver-filled one component polyimide adhesive which is characterized by its high temperature resistance. Elecolit[®] 327 has excellent adhesion to gold, aluminum, tantalum, germanium and ceramic substrates.

Note: n-Methylpyrollidone dissolves most plastics, so the processing equipment should be glass, stainless steel, polyethylene or polypropylene.

Curing Properties

The product is a one-component adhesive and can be cured with the addition of heat. Possible curing temperatures are listed in the table below.

Thermal curing		
Time at 120°C	4h	
Time at 150°C	1h	

After thermal curing the product must be postcured for 2 h at 200 ° C.

The curing times given are guidelines. They refer to the curing of 2 g of adhesive. The heating up of the joining members are not taken into account.

The final strength of the adhesive is reached at the earliest after 24 h.

Technical Data

Resin polyimide Appearance grey Filler — weight [%] sliver

Uncured material

Viscosity [mPas]	paste-like
Dichte [g/cm³] PE-Norm 004	3,2

Technical Datasheet Elecolit® 327



Cured material

Temperature resistance [°C] PE-Norm 065	-45 - 275
Coefficient of linear expansion [ppm/K] below Tg PE-Norm 017	27,0
The second construction is a DAV/control	
Thermal conductivity [W/m*K] PE-Norm 062	4,1
Volume resistivity [Ohm*cm] PE-Norm 040	0,0001

Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Other packages	0°C - 10°C	0°C - 10°C	at delivery min. 6 months max. 12 months

^{*}Store in original, unopened containers!

Instructions for Use

Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP[®] Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

For safety information refer to our safety data sheet.

Technical Datasheet

Elecolit® 327



Note

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2011/65/EU "RoHS II" .

Our data sheets have been compiled to the best of our knowledge. The enclosed information describes characteristic properties, with no declaration of commitment. We recommend trials in order to confirm that our products satisfy the particular application requirements. For any additional technical support, please contact our application engineering department. For warranty claims, please refer to our standard terms and conditions.